Marked-up Specification

TITLE

Al/Cu/Mg/Ag alloy with Si, semi-finished product from such an alloy as well as method for the production of such a semi-finished product

CROSS REFERENCE APPLICATIONS

This application is a national phase application claiming priority from PCT application no. PCT/EP2002/07193 filed on 29 June 2002.

FIELD OF INVENTION

Subject matter of the invention is an Al/Cu/Mg/Mn ~~Alloy~~ alloy for the production of semi-finished products with high static and dynamic strength properties. The invention further relates to semi-finished products manufactured from such an alloy with high static and dynamic strength properties as well as to a method for the production of such a semi-finished product.

BACKGROUND OF THE INVENTION

Aluminum alloys having a high static and dynamic bearing capacity~~, are for example~~ include the alloys AA 2014 and AA 2214. ~~From these Al alloys in the artificially aged state for example drop~~Drop-forged parts for wheel and brake systems of airplanes are manufactured from these Al alloys in the artificially aged state~~are manufactured~~. ~~While the listed strength properties of the~~ The semi-finished products produced ~~of such an~~from the alloy intrinsically have the listed strength properties of ~~are~~ the alloys ~~an intrinsic characteristic of the semifinished product~~, especially at lower temperatures~~,~~. However, at temperatures of more than

100° C these properties decrease more rapidly than is the case with alloys of the group AA 2618.

Semi-finished products of ~~such~~ the alloys of group AA 2618 have better high-temperature stability and are utilized ~~for example~~ for a variety of uses such as compressor impellers for rechargeable ~~Diesel~~ diesel engines or for rotors of ultracentrifuges. However, at temperatures below 100°C, the aluminum alloys of the group AA 2014 and AA 2214 have greater bearing capacity.

In ~~the case of~~ the wheel brake system of airplanes considerable heat is generated during the braking process. This leads to temperature increases even in the wheels, which typically are fabricated of an AA 2014 or AA 2214 alloy. These can cause early overageing of this alloy and~~, entailed therein,~~ lead to a severe limitation of the service life of the structural part.

In ~~the case of~~ compressor impellers the transition~~s~~ to titanium alloys ~~have~~ has been made ~~in order~~ to ~~lend~~ give the compressor impellers ~~produced therefrom~~ the necessary static and dynamic strength properties even at increased temperatures. However, employing titanium is expensive ~~and especially for this reason~~ is therefore not suitable for the production of airplane wheels. Furthermore, titanium is less well suited as a material for wheels due to its limited thermal conductivity~~, titanium is less well suited as a material for wheels~~.

The problematic described above is not new. Therefore, for many years there has been the wish for an Al alloy, which combines the high strength properties of the alloys AA 2014 or AA 2214 at ambient temperature and the thermal stability of the alloys AA 2618 or 2618 A.

10/501574

DT04 Rec'd PCT/PTO 13 JUL 2004

SUMMARY OF THE INVENTION

The invention therefore addresses the problem of providing such an alloy, a semi-finished product produced of such an alloy with high static and dynamic bearing capacity, high thermal stability, high fracture toughness and high creep resistance as well as a method for the production of such semi-finished products.

Other aspects of this invention will appear from the following description and appended claims, reference being made to the accompanying drawings forming a part of this specification wherein like reference characters designate corresponding parts in the several views.

This problem is solved according to the invention ~~thereby that~~with an ~~the~~ alloy that has the following composition:

0.3 - 0.7 wt. % silicon (Si)
maximally 0.15 wt. % iron (Fe)
3.5 - 4.5 wt. % copper (Cu)
0.1 - 0.5 wt. % manganese (Mn)
0.3 - 0.8 wt. % magnesium (Mg)
0.05 - 0.15 wt. % titanium (Ti)
0.1 - 0.25 wt. % zirconium (Zr)
0.3 - 0.7 wt. % silver (Ag)
maximally 0.05 wt. % other, individually
maximally 0.15 wt. % other, total
remaining wt. % aluminum (Al).

Compared to the prior known alloys AA 2014 and AA 2214, the claimed alloy has higher static and dynamic thermal stability and improved creep resistance ~~with~~

~~simultaneously~~while also having very good mechanical fracturing properties. These properites are attained in particular at a copper-magnesium ratio between 5 and 9.5, in particular at a ratio between 6.3 and 9.3. The copper content is preferably between 3.8 and 4.2 wt. % and the magnesium content between 0.45 and 0.6 wt. %. The copper content is markedly below the maximum solubility for copper in the presence of the claimed magnesium content. As a consequence, the fraction of insoluble copper-containing phases is very low, also taking into consideration the remaining alloy and companion elements. Thereby an improvement is obtained with respect to the dynamic properties and the fracture toughness of the semi-finished products manufactured from such an alloy.

In contrast to the known AA alloys 2014 and 2219, a portion of the claimed alloy is silver with contents between 0.3 and 0.7 wt. %, preferably 0.45 and 0.6 wt. %. In the interaction with silicon (0.3 - 0.7 wt. %, preferably 0.4 - 0.6 wt. %) the hardening takes place via the same mechanisms as in silver-free Al/Cu/Mg alloys. However, it has been found that with lower silicon contents, the course of precipitation is different due to the addition of silver.

While the semi-finished products manufactured from such an alloy have good high-temperature stability and creep resistances under cooler conditions, ~~however,~~ they do not meet the desired requirements. Only silicon contents above 0.3 wt. % suppress the otherwise typical change of the precipitation behavior of Al/Cu/Mg/Ag alloys, such that unexpectedly higher strength values can be attained without having to give up the high-temperature stability and the

creep resistance with the Cu and Mg contents according to the invention.

The manganese content of the claimed alloy is 0.1 to 0.5 wt. %, preferably 0.2 - 0.4 wt. %. In the case of alloys with higher manganese contents undesirable precipitation processes were found with long-term high-temperature stress, which led to a decrease of strength. For this reason the manganese content is limited to 0.4 wt. %. However, manganese is fundamentally required as an alloy component ~~fundamentally required~~ for the control of the grain structure.

To balance the reducing effect of ~~managese~~manganese with respect to the grain structure control, the alloy contains zirconium between 0.10 - 0.25 wt. %, preferably 0.14 - 0.20 wt. %. The precipitating zirconium aluminides, as a rule, are developed even more finely dispersed than manganese aluminides. Moreover, ~~It~~it was ~~moreover~~ found that the zirconium aluminides contribute to the thermal stability of the alloy.

For grain sizing 0.05 - 0.15 wt. %, preferably 0.10 - 0.15 wt. % of titanium is added. The titanium is usefully added in the form of an Al/5Ti/1B prealloy, whereby boron is automatically included in the alloy. ~~Therefrom finely~~ Finely dispersed, insoluble titanium diborides are formed therefrom. These contribute to the thermal stability of the alloy.

The alloy can comprise maximally 0.15 % iron, preferably 0.10%, as an unavoidable contamination.

~~In the following, test results will be described with reference to the attached figures. These depict:~~

BRIEF DESCRIPTION OF THE DRAWINGS

Fig. 1 is a ~~diagram representing~~graph showing the 0.2% yield strength and the tensile strength of the alloy according to the invention in state T6 in comparison to prior known alloys, as a function of the test temperature.~~,~~

Fig. 2 is a ~~diagram representing~~graph showing the long-time stress to rupture strength of the alloy according to the invention in state T6 in comparison to known alloys~~,~~.

Fig. 3 is a ~~diagram representing~~graph showing the 0.2% yield strength and the tensile strength of airplane wheels manufactured from the alloy according to the invention in comparison to such manufactured from known alloys~~,~~. ~~and~~

Figs. 4a and 4b are ~~diagrams~~ graphs ~~representing~~ showing the fatigue strength of the alloy according to the invention in comparison to a known alloy in state T6 at ambient temperature and at a temperature of 200° C.

Before explaining the disclosed embodiment of the present invention in detail, it is to be understood that the invention is not limited in its application to the details of the particular arrangement shown, since the invention is capable of other embodiments. Also, the terminology used herein is for the purpose of description and not of limitation.

DETAILED DESCRIPTION OF THE INVENTION

Table 1 reproduced below shows the chemical composition of four alloys (B, C, D, E) according to the invention as well as the composition of the alloys AA 2214 and AA 2618 examined as a comparison (data in wt. % (n.d.: not determined)

Table 1

Alloy	Si	Fe	Cu	Mn	Mg	Ni	Zn	Ti	Ag	Zr	V
B	0.47	0.08	4.40	0.200	0.58	0.003	0.048	0.135	0.45	0.150	0.018
C	0.47	0.08	3.64	0.210	0.59	0.003	0.015	0.115	0.52	0.150	0.017
D	0.47	0.08	3.87	0.200	0.61	0.003	0.015	0.117	0.52	0.150	0.019
E	0.52	0.08	4.14	0.200	0.61	0.003	0.02	0.115	0.44	0.150	0.018
AA 2214	0.77	0.17	4.29	0.883	0.57	0.003	0.031	0.024	0.003	0.007	n.d.
AA 2618	0.22	1.1	2.58	0.020	1.53	1.007	0.043	0.059	0.003	0.002	n.d.

From these alloys semi-finished products were manufactured following the method steps listed below:

a) casting of an ingot from an alloy,

b) homogenizing the cast ingot at a temperature, which is as close under the incipient melting temperature of the alloy as is possible, for a length of time adequate to attain maximally uniform distribution of the alloy elements in the cast structure,

c) hot working of the homogenized ingot by forging at a block temperature of approximately 420°C,

d) solution treatment of the semi-finished product worked by forging at temperatures sufficiently high to bring the alloy elements necessary for the hardening into solution such that they are uniformly distributed in the structure, with the solution treatment taking place in a temperature range ~~[sic]~~ of 505°C over a time period of 3 hours,

e) quenching of the solution-treated semi-finished product in water at ambient temperature,

f) cold working of the quenched semi-finished products by cold upsetting by 1 to 2%, and

g) artificial ageing of the quenched semi-finished product at a temperature of 170°C over time period of 20 to 25 hours.

The open-die forged pieces produced in this manner were subsequently tested for their properties in the ~~artifically~~artificially aged state T6.

Table 2

Strength values at ambient temperature **Fracture toughness at ambient temp.**

Alloy	Sample direction	R_{p02} (MPa)	R_m (MPa)	A_5 (%)	Sample direction	K_{IC} (MPa$\sqrt{m}$)
C	L LT ST	448 427 417	485 471 479	11.2 7.2 6.3	T-L S-L S-T	31.3 29.5 32.2
D	L LT ST	456 434 429	495 478 484	10.7 8.0 5.5	T-L S-L S-T	28.3 29.1 29.6
E	L LT ST	454 446 438	494 493 494	9.9 6.4 4.9	T-L S-L S-T	26.1 25.5 26.9
AA 2214	L LT ST	444 439 429	489 483 480	9.7 6.4 5.8	T-L S-L S-T	24.2 25.9 27.3

AA 2219	L LT ST	286 288 366	408 403 455	16.7 8.4 5.0	T-L S-L S-T	31.1 34.4 32.3
AA 2618	L LT ST	389 383 376	443 437 427	5.1 4.7 4.1	T-L S-L S-T	19.2 16.7 19.3

Table 3

Alloy		***E***			***AA 2214***			***AA 2618***		
R_{test} (°C)	T_{hold} (h)	R_{p02} (Mpa)	R_m (Mpa)	A_5 (%)	R_{p02} (Mpa)	R_m (Mpa)	A_5 (%)	R_{p02} (Mpa)	R_m (Mpa)	A_5 (%)
20	1	454	494	9.9	444	489	9.6	380	434	6.5
50	1	453	493	12.6	443	485	9.8	382	433	6.1
100	1	449	474	13	425	458	11	374	423	6.5
150	1	404	417	14.3	403	424	13.6	366	404	7.6
170	1	403	416	16.3	382	400	13.6	382	389	9.6
200	1	355	372	18	348	368	13.8	340	359	12.2
220	1	340	351	18	324	344	14.2	301	332	12.4
250	1	268	282	19	250	268	16.1	282	300	14.7

Definitions sample directions:
L= longitudinal direction: parallel to the main form change direction
LT= long transverse direction: parallel to the width direction
ST= short transverse direction: parallel to the thickness direction

The improved strengths of the alloy according to the invention (for example alloy E) is clearly evident in Tables 2 and 3. For example, while the prior known alloy AA 2214 shows good strength values at ambient temperature, ~~however~~ it

does not at higher temperatures~~ it does not~~. Moreover, the creep resistance ~~as well as~~and the fracture toughness are ~~not only~~ markedly better at ambient temperature~~, but especially also~~ and at higher temperatures~~,~~ in the claimed alloy ~~than in~~compared to the prior known alloys. This comparison makes ~~further~~ clear that the tested prior known alloys have ~~only~~ good properties only with respect to a single strength parameter. ~~Not in~~ In no ~~a single~~ case do ~~these~~ the prior alloys have good properties in all relevant strength values at ambient temperature as well as ~~also~~ at increased temperatures. Just as is the case with the fatigue properties, the creep resistance of this prior known alloy is not satisfactory. Very good properties over all tested strength parameters could only be determined in the case of the alloy according to the invention.

~~The associated representation of~~ Figure 1 also makes graphically clear the better strength properties of the alloy (alloy E) according to the invention compared to the known alloys (AA 2214 as well as AA 2618). The results showed unexpectedly that the strength values of alloy E are better even at temperatures below 100°C than those of the known alloy AA 2214, which is known for its especially high strength values in this temperature range.

~~Moreover~~Additionally, the creep resistance of the semi-finished products was tested. Table 4 shown below provides the test results (LMP: Larson Miller parameter) in summary:

Table 4:

Alloy											
E				AA 2214				AA 2618			
T_{test}	σ_{test}	$t_{fracture}$	LMP	T_{test}	σ_{test}	$t_{fracture}$	LMP	T_{test}	σ_{test}	$t_{fracture}$	LMP

(°C)	(MPa)	(h)	(-)	(°C)	(MPa)	(h)	(-)	(°C)	(MPa)	(h)	(-)
180	185	2513	10.60	205	200	30	10.27	205	183	10	10.04
	167	4762	10.82		190	50	10.38		179	50	10.38
					181	100	10.52		175	100	10.52
					130	500	10.85		163	500	10.85
					100	800	10.95		159	1000	11.00

Plotted graphically, the markedly better long-time stress to rupture strength of the alloy in the T6 state in comparison to the known alloys AA 2214 and AA 2618 ~~also~~ in the T6 state is apparent. This is ~~reproduced in the diagram of~~shown in Figure 2 as time-compensated temperature representation. The especially good creep resistance of the alloy according to the invention could not be foreseen~~, such that~~ making this result ~~is~~ surprising.

Within the scope of testing the method steps for the production of these semi-finished products, it was found that comparable material properties of the produced semi-finished products can be attained if the step of hot working is carried out at a block temperature between 320°C to 460°C. The hot working can be either forging or rolling. The step of quenching of the solution treated semi-finished product can take place in a temperature range between ambient temperature and 100°C (boiling) in water. It is also possible to utilize a water-glycol mixture for the quenching, the temperature of which~~, however,~~ should not exceed 50°C.

~~Instead of the previously described step of cold working through cold upsetting during forging, as a~~A cold working step ~~also~~ of a drawing out by 1% to 5% can be carried out in the case of extruded or rolled products for the purpose of

reducing the intrinsic stresses due to the quenching instead of the previously described step of cold working through cold upsetting during forging. The step of artificial ageing can be carried out over a time period of 5 to 35 hours, preferably between 10 and 25 hours, in a temperature window between 170°C and 210 °C.

During further tests strand-cast ingots were produced as described above and airplane wheels manufactured by drop forging in the preforge die and finish forge die at a temperature of 410 to 430°C. These wheels were subsequently solution treated at 505°C, quenched in a mixture of water and glycol of ambient temperature and thermally age-hardened at 170°C for 20 hours. ~~For~~ These were ~~compari~~compared to ~~son~~ mass-produced airplane wheels of the alloy AA 2214~~were used~~. Samples were taken from the wheels produced of the claimed alloy and of the conventional alloy ~~At~~ at sites distributed over the circumference~~samples were removed from the wheels produced of the claimed alloy and of the conventional alloy~~, and tested for their tensile strength. The results ~~is~~are ~~graphically~~ shown in Figure 3. It can ~~be~~ clearly be seen that the alloy E according to the invention yields better values compared to the known alloy AA 2214.

Fatigue tests in comparable samples of the two cited alloys also show that the wheels produced from the claimed alloy attain markedly better values than the wheels produced from the alloy AA 2214. This applies to the fatigue tests carried out at ambient temperature (cf. Figure 4a) as well as to the fatigue tests carried out at a test temperature of 200°C (cf. Figure 4b).

The description of the claimed invention ~~surprisingly~~ makes clear that surprisingly ~~these~~ the claimed alloys have

not only high dynamic and static strength values, but that ~~these~~ they have ~~in particular also~~ an especially good high-temperature stability, fracture toughness and creep resistance. ~~Therefore this~~ This alloy is therefore ~~is in~~ particularly suitable for the production of semi-finished products, which must meet precisely these requirements, such as ~~for example~~ airplane wheels or compressors.

Although the present invention has been described with reference to the disclosed embodiments, numerous modifications and variations can be made and still the result will come within the scope of the invention. No limitation with respect to the specific embodiments disclosed herein is intended or should be inferred. Each apparatus embodiment described herein has numerous equivalents.

10/501574
DT04 Rec'd PCT/PTO 13 JUL 2004

ABSTRACT

An Al/Cu/Mg/Mn alloy for the production of semi-finished products with high static and dynamic strength properties has the following composition: 0.3-0.7 wt % silicon (Si), max. 0.15 wt.% iron (Fe), 3.5-4.5 wt % copper (Cu), 0.1-0.5 wt. % manganese (Mn), 0.3-0.8 wt. % magnesium (Mg), 0.5-0.15 wt % titanium (Ti), 0.1-0.25 wt % zirconium (Zr), 0.3-0.7 wt. % silver (Ag), max. 0.05 wt. % others individually, max 0.15 wt. % others globally, the remaining wt. % aluminum (Al). The invention further relates to a semi-finished product made for such an alloy and a method of production of a semi-finished product made for such an alloy.